

Sinpolene FRF2074

Polypropylene

Teknor Apex Asia Pacific PTE. LTD.

Message:

Sinpolene FRF2074 is a Polypropylene material. It is available in Africa & Middle East, Asia Pacific, or Latin America.

Important attributes of Sinpolene FRF2074 are:

Flame Rated

Flame Retardant

Typical applications include:

Appliances

Housings

General Information			
UL YellowCard	E142591-223225		
Additive	Flame Retardant		
Features	Flame Retardant		
Uses	Appliance Components		
	Housings		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.936	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.013	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	87		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	38.0	MPa	ASTM D638
Flexural Modulus	1300	MPa	ASTM D790
Flexural Strength	40.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	25	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	105	°C	ASTM D648
Vicat Softening Temperature	154	°C	ASTM D1525 ¹
Flammability	Nominal Value	Test Method	
Flame Rating (1.60 mm)	V-2	UL 94	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

