

ELIX™ ABS M203FC

Acrylonitrile Butadiene Styrene

ELIX Polymers, S. L.

Message:

ELIX ABS M203FC
Injection Moulding grade for medical applications (e.g. inhalers, roller clamps, spikes, etc.)/ Biocompatible with up to 30 days human contact duration according to USP Class VI and ISO 10993-1. Food contact acc. to BfR and FDA, DMF registered. Easy flowing, high gloss, standard impact strength.
ISO Shortname: ISO 2580-ABS 0,MG,095-25-16-25

General Information			
UL YellowCard	E350602-101011285		
Features	Biocompatible		
	Food Contact Acceptable		
	Good Flow		
	Good Impact Resistance		
	High Gloss		
Uses	Medical/Healthcare Applications		
Agency Ratings	BfR Food Contact, Unspecified Rating		
	DMF Unspecified Rating		
	FDA Food Contact, Unspecified Rating		
	ISO 10993-Part 1		
	USP Class VI		
Forms	Pellets		
Processing Method	Injection Molding		
Part Marking Code (ISO 2580)	ABS 0,MG,095-25-16-25		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	31.0	cm ³ /10min	ISO 1133
Molding Shrinkage ¹			ISO 294-4
Across Flow	0.40 to 0.70	%	
Flow	0.40 to 0.70	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	110	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2400	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	46.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield, 23°C	2.6	%	

Break, 23°C	> 15	%	
Flexural Modulus ² (23°C)	2400	MPa	ISO 178
Flexural Stress ³ (23°C)	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	7.0	kJ/m ²	
23°C	15	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	90	kJ/m ²	
23°C	110	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-30°C	7.0	kJ/m ²	
23°C	15	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	98.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	94.0	°C	ISO 75-2/A
Vicat Softening Temperature	99.0	°C	ISO 306/B50
CLTE - Flow (23 to 55°C)	9.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	35	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.00		
23°C, 1 MHz	2.90		
Dissipation Factor			IEC 60250
23°C, 100 Hz	5.0E-3		
23°C, 1 MHz	9.0E-3		
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate ⁴ (2.00 mm)	60	mm/min	ISO 3795
Glow Wire Flammability Index (2.00 mm)	700	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	Test Method
Processing (Melt) Temp	240	°C	
Mold Temperature	70.0	°C	
Injection Velocity	240	mm/sec	ISO 294
NOTE			
1.	60x60x2		
2.	2.0 mm/min		
3.	2.0 mm/min		
4.	US - FMVSS		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

