

Fusabond® P613

Polypropylene

DuPont Packaging & Industrial Polymers

Message:

DuPont™ Fusabond® P613 is a anhydride modified polypropylene.

Uses:

Polymer Modifier

Applications: Coupling agent, short glass fiber filled PP

General Information			
Filler / Reinforcement	Glass Fiber		
Uses	Blending		
Agency Ratings	FDA 21 CFR 175.105		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.903	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238, ISO 1133
190°C/1.0 kg	49	g/10 min	
190°C/2.16 kg ¹	120	g/10 min	
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	162	°C	ASTM D3418, ISO 3146
Additional Information	Nominal Value	Unit	
Processing Temperature	< 300	°C	
NOTE			
1.	estimated value		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

