

POLYelast TPE S906

Styrene Butadiene Styrene Block Copolymer

Polykemi AB

Message:

SBS-based

General Information			
Physical	Nominal Value	Unit	Test Method
Density	1.15	g/cm³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	1.4 to 2.0	%	
Flow	1.4 to 2.0	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	90		ASTM D2240
Thermal	Nominal Value	Unit	
Service Temperature	-50 to 65	°C	
Ozone and Weather Resistance	+		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT