

SUPRAN® WLFT 311BL

Thermoplastic

SAMBARK

Message:

WLFT 311BL is a new material of sheet that is hybridized with fully impregnated WFT (Woven Fiber-glass Thermoplastic-mat) and LFT (Long Fiber Thermoplastics) sheets. WLFT 311BL is suitable for various parts in automotives, construction and industry applications as new materials to replace metals.

General Information			
Filler / Reinforcement	Glass Fabric		
	Long Glass Fiber		
Uses	Automotive Applications		
	Construction Applications		
	Industrial Applications		
	Metal Replacement		
	Sheet		
	Structural Parts		
Forms	Sheet		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	118	MPa	ASTM D638
Flexural Modulus	5640	MPa	ASTM D790
Flexural Strength	164	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C	1500	J/m	
23°C	980	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	163	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

