

# RANPELEN SFC-750R

Polypropylene Random Copolymer

Lotte Chemical Corporation

Message:

RANPELEN SFC-750R is a controlled medium modified polypropylene random copolymer designed for cast film technology. It offers an excellent clarity and gloss, a very low haze, a wide hot tack range, roll mark free and a low Heat seal temperature of 120°C. It is designed for quality packaging applications, as heat seal layer film. RANPELEN SFC-750R is easy processable on commercial cast film equipment. It contains slip and antiblock additives. RANPELEN SFC-750R is suitable for food contact.

General Information			
Additive	Antiblock		
	Slip		
Features	Antiblocking		
	Food Contact Acceptable		
	High Clarity		
	High Gloss		
	Low Temperature Heat Sealability		
	Random Copolymer		
	Slip		
Uses	Cast Film		
	Film		
	Packaging		
Processing Method	Cast Film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm <sup>3</sup>	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ASTM D1238, ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	82		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	22.6	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	> 500	%	ASTM D638, ISO 527-2
Flexural Modulus	785	MPa	ASTM D790, ISO 178
Coefficient of Friction (Cast Film)	< 1.0		Internal Method
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	98	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	70.0	°C	ASTM D648, ISO 75-2/B

Melting Temperature			
--	131	°C	Internal Method
--	132	°C	ASTM D3418
Optical	Nominal Value	Unit	Test Method
Haze (30.0 μm, Cast Film)	< 2.0	%	ASTM D1003
Additional Information	Nominal Value	Unit	Test Method
Heat Seal Temperature <sup>1</sup> (30.0 μm)	120	°C	Internal Method
NOTE			
1.	Cast Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

