

# Moplen HP563S

Polypropylene Homopolymer

PolyMirae

## Message:

Moplen HP563S is the controlled rheology polypropylene homopolymer manufactured by PMC under the license of BASELL using the Spheripol process. Moplen HP563S is a homopolymer typically used in spunbonded nonwovens. Moplen HP563S resin meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.

General Information			
Features	Food Contact Acceptable		
	Good Colorability		
	Good Processability		
	Good Processing Stability		
	Good Stiffness		
	Good Surface Finish		
	Good Toughness		
	High Gloss		
	Homopolymer		
	Low Warpage		
Uses	Closures		
	Household Goods		
	Packaging		
	Toys		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	38	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	98		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Injection Molded)	37.3	MPa	ASTM D638
Tensile Elongation (Yield, Injection Molded)	8.0	%	ASTM D638
Flexural Modulus (Injection Molded)	1470	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	29	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed, Injection Molded)	100	°C	ASTM D648
--	-----	----	-----------

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
 Phone: +86 13424755533  
 Email: sales@su-jiao.com  
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

