

APEX® 80328-Y

Flexible Polyvinyl Chloride

Teknor Apex Company

Message:

APEX® 80328-Y is a Flexible Polyvinyl Chloride material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Important attributes of APEX® 80328-Y are:
RoHS Compliant
Sunlight Resistant
Typical application of APEX® 80328-Y: Wire & Cable

General Information			
Features	Sunlight Resistant (720 hours)		
Uses	Cable Jacketing		
	Insulation		
Wire Types	TW		
Agency Ratings	UL QMTT2 .E73402		
RoHS Compliance	RoHS Compliant		
Appearance	Opaque		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	85		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	16.5	MPa	ASTM D638
Tensile Elongation (Break)	320	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	75.0	°C	ASTM D794
Brittleness Temperature	-29.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	5.19		
1 MHz	3.58		
Dissipation Factor			IEC 60250
1 kHz	0.070		
1 MHz	0.068		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	23	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT