

NILFLEX® 8 K30T

Polypropylene Copolymer

Taro Plast S.p.A.

Message:

Polypropylene copolymer medium flow 30% mineral filled, high impact, good surface appearance.

General Information			
Filler / Reinforcement	Mineral filler, 30% filler by weight		
Features	Copolymer		
	Impact resistance, high		
	Medium liquidity		
	Good appearance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction	0.80 - 1.3	%	Internal method
Flow direction	0.80 - 1.3	%	Internal method
Water Absorption (23°C, 24 hr)	0.020	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	23.0	MPa	ISO 527-2/50
Tensile Strain (Break)	50	%	ISO 527-2/50
Flexural Modulus ¹	1900	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Unnotched Izod Impact (0°C)	65	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	62.0	°C	ISO 75-2/A
Vicat Softening Temperature	75.0	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Burning Rate ²	< 150	mm/min	ISO 3795
Flame Rating			UL 94
1.60 mm	HB		UL 94
3.20 mm	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 - 230	°C	
Mold Temperature	40.0 - 60.0	°C	

Injection Rate	Moderate
Injection instructions	
Pre-heat Temperature: 70 to 80°CPre-heat Time: 1 hr	
NOTE	
1.	1.0 mm/min
2.	US FMVSS302

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

