

Stanyl® TE250F8

Polyamide 46
DSM Engineering Plastics

Message:

Stanyl® TE250F8 is a Polyamide 46 (Nylon 46) material filled with 40% glass fiber. It is available in Asia Pacific or Europe.
Important attributes of Stanyl® TE250F8 are:
Flame Rated
Flame Retardant
Heat Stabilizer

General Information				
UL YellowCard	E43392-235033	E47960-240065	E172082-359025	
Filler / Reinforcement	Glass Fiber,40% Filler by Weight			
Additive	Flame Retardant			
	Heat Stabilizer			
Features	Flame Retardant			
	Heat Stabilized			
Forms	Pellets			
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)			
	Secant Modulus vs. Strain (ISO 11403-1)			
	Shear Modulus vs. Temperature (ISO 11403-1)			
	Viscosity vs. Shear Rate (ISO 11403-2)			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.77	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.90	--	%	
Flow	0.30	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.3	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2
--	15000	12000	MPa	
120°C	9500	--	MPa	
160°C	6500	--	MPa	
Tensile Stress				ISO 527-2
Break	180	130	MPa	
Break, 120°C	100	--	MPa	
Break, 160°C	85.0	--	MPa	
Tensile Strain				ISO 527-2

Break	1.9	2.5	%	
Break, 120°C	3.0	--	%	
Break, 160°C	3.0	--	%	
Flexural Modulus				ISO 178
--	13000	11000	MPa	
120°C	8500	--	MPa	
160°C	5500	--	MPa	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	13	13	kJ/m ²	
23°C	13	14	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	40	40	kJ/m ²	
23°C	50	50	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
-40°C	14	14	kJ/m ²	
23°C	14	15	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	290	--	°C	ISO 75-2/A
Melting Temperature ¹	295	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	2.5E-5	--	cm/cm/°C	
Transverse	5.0E-5	--	cm/cm/°C	
Thermal Index - 5000 hrs	163	--	°C	IEC 60216
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+10	ohms·cm	IEC 60093
Electric Strength	30	20	kV/mm	IEC 60243-1
Comparative Tracking Index	325	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.350 mm	V-0	--		
1.50 mm	V-0	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	280 to 320		°C	
Middle Temperature	300 to 320		°C	
Front Temperature	300 to 320		°C	

Nozzle Temperature	300 to 320	°C
Processing (Melt) Temp	305 to 320	°C
Mold Temperature	80.0 to 120	°C
Injection Rate	Moderate-Fast	
Back Pressure	2.00 to 10.0	MPa
Screw Compression Ratio	2.5:1.0	

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT