

RTP 1000 UV

Polybutylene Terephthalate

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Additive	UV stabilizer		
Features	Good UV resistance		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.8	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ASTM D638
Tensile Strength	48.3	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	2070	MPa	ASTM D790
Flexural Strength	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1100	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	149	°C	ASTM D648
1.8 MPa, not annealed	48.9	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Additional Information			
The value listed as Flammability, UL 94, was tested in accordance with RTP test standards.Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 22mil/in.Tensile Elongation, ASTM D-638: 10+%			

Injection	Nominal Value	Unit
Drying Temperature	121	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.030	%
Suggested Max Regrind	20	%
Rear Temperature	232 - 271	°C
Middle Temperature	232 - 271	°C
Front Temperature	232 - 271	°C
Mold Temperature	37.8 - 121	°C
Injection Pressure	68.9 - 103	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

