Petrothene® GS707062

Linear Low Density Polyethylene

LyondellBasell Industries

Message:

The PETROTHENE SELECT series of resins are pelletized, high performance hexene, linear low density polyethylenes for applications requiring superior strength and toughness. These products offer significant improvements in mechanical properties and excellent additive homogeneity without sacrificing processability. Applications include trash and can liners, commercial and industrial packaging, as well as consumer packaging. The PETROTHENE SELECT series resins offer enhanced film strength, drawdown, toughness and heat seal strength

General Information					
Additive	Medium Antiblock (12%)				
	Medium Slip (1350 ppm)				
Features	Food Contact Acceptable				
	Good Drawdown				
	Good Heat Seal				
	Good Processability				
	Good Strength				
	Low Density				
	Ultra High Toughness				
Uses	Consumer Applications				
	Industrial Applications				
	Liners				
	Packaging				
Agency Ratings	FDA 21 CFR 177.1520				
Forms	Pellets				
Processing Method	Film Extrusion				
Physical	Nominal Value	Unit	Test Method		
Density	0.924	g/cm³	ASTM D1505		
Melt Mass-Flow Rate (MFR) (190°C/2.16	0.70				
kg)	0.70	g/10 min	ASTM D1238		
Films	Nominal Value	Unit	Test Method		
Film Thickness - Tested	25	μm			
Secant Modulus			ASTM D882		
1% Secant, MD : 25 μm, Blown Film	193	MPa			
1% Secant, TD : 25 μm, Blown Film	200	MPa			
Tensile Strength			ASTM D882		
MD : Break, 25 µm,Blown Film	58.6	MPa			
TD : Break, 25 µm,Blown Film	44.8	MPa			

Tensile Elongation			ASTM D882
MD : Break, 25 µm,Blown Film	530	%	
TD : Break, 25 µm,Blown Film	680	%	
Dart Drop Impact (25 µm, Blown Film)	750	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm, Blown Film	350	g	
TD : 25 μm, Blown Film	580	g	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

