# **TERRAMAC TE-8210**

### Polylactic Acid

#### **UNITIKA Plastics Division**

#### Message:

TERRAMAC TE-8210 is a Polylactic Acid (PLA) material. It is available in Asia Pacific, Europe, or North America for injection molding. Important attributes of TERRAMAC TE-8210 are: Eco-Friendly/Green Wear Resistant Typical applications include: Business/Office Goods Consumer Goods Containers Electrical/Electronic Applications Trays/Racks

General Information				
Features	Biodegradable			
	Durable			
	Renewable Resource Content			
Uses	Consumer Applications			
	Containers			
	Electrical/Electronic Applications			
	Stationary Supplies			
	Support Trays			
Appearance	Opaque			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	1.42	g/cm³	ISO 1183	
Molding Shrinkage	1.0 to 1.2	%	ISO 294-4	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Stress (Break)	50.0	MPa	ISO 527-2	
Tensile Strain (Break)	2.0	%	ISO 527-2	
Flexural Modulus	6800	MPa	ISO 178	
Flexural Stress	90.0	MPa	ISO 178	
Impact	Nominal Value	Unit	Test Method	
Charpy Notched Impact Strength	4.0	kJ/m²	ISO 179	
Thermal	Nominal Value	Unit	Test Method	
Heat Deflection Temperature (0.45 MPa,				
Unannealed)	120	°C	ISO 75-2/B	
Melting Temperature	170	°C		

Injection	Nominal Value	Unit
Rear Temperature	150 to 170	°C
Middle Temperature	180 to 200	℃
Front Temperature	190 to 210	°C
Nozzle Temperature	190 to 210	°C
Processing (Melt) Temp	< 240	°C
Mold Temperature	100 to 110	°C
Back Pressure	0.490 to 1.47	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

