

SCHULABLEND® (PA/PP) M/MO GF 25

Polyamide + PP
A. Schulman Europe

Message:
25% glass fibre reinforced PA/PP blend with excellent chemical resistance

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 25% filler by weight		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PA6+PP-GF		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	4.00	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	108	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6700	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	103	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	%	ISO 527-2/1A/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	6.0	kJ/m ²	ISO 179/1eA
23°C	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	55	kJ/m ²	ISO 179/1eU
23°C	45	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	184	°C	ISO 75-2/Bf
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (1.60 mm)	HB		IEC 60695-11-10, -20
Additional Information			

- 1.)
- Not for use in food contact applications2.)
- Not for use in medical or pharmaceutical applications

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT