# Geon™ Vinyl Wire & Cable WE2010

### Flexible Polyvinyl Chloride

PolyOne Corporation

#### Message:

Geon™Vinyl Wire & Cable WE2010 is a flexible PVC product. It can be processed by extrusion coating and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: wire and cable. The main features are: Rohs certification.

General Information			
Uses	Wire and cable applications		
	Insulating material		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Extrusion coating		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	56		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	22.8	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	350	%	ASTM D638
Aging	Nominal Value	Unit	
Tensile strength retention rate <sup>3</sup> (136°C, 762.0 µm)	80	%	
Elongation retention rate <sup>4</sup> (136°C, 762.0			
μm)	65	%	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-7.00	°C	ASTM D746
UL Temperature Rating	105	°C	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index (3.18 mm)	33	%	ASTM D2863
Additional Information			
NOTE: Typical Properties of Molded Slab (0.075"); Not to be Construed as Specifications.			
Extrusion	Nominal Value	Unit	
Melt Temperature	177 - 188	°C	
NOTE			
1.	Type 4, 510mm/min		
2.	Type 4, 510mm/min		
3.	168 hr, UL Standard		
4.	168 hr, UL Standard		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

