

Hifax HSBM CB1158ACLS/3

Thermoplastic Polyolefin Elastomer
LyondellBasell Industries

Message:

Hifax HSBMCB1158ACLS/3 high melt flow, 1,200 MPa flexural modulus, mineral filled thermoplastic elastomeric olefin (TEO) resin has a unique balance of flow, rigidity, and paintability. It was designed primarily for thin-walled bumper fascia applications.

General Information			
Filler / Reinforcement	Mineral		
Features	Good Dimensional Stability		
	Good Flow		
	Good Moldability		
	Good Stiffness		
	High Impact Resistance		
	Low Temperature Impact Resistance		
	Medium Rigidity		
	Paintable		
Uses	Automotive Bumper		
	Automotive Exterior Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.980	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238, ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	18.0	MPa	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2
Flexural Modulus	1200	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	85.0	°C	ISO 75-2/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

