

Kemcor HD 0892

High Density (HMW) Polyethylene

Qenos Pty Ltd

Message:

This resin meets the requirements for unrestricted food contact specified in AS 2070 Part 1 (1992).

General Information	
Additive	Antioxidant
Features	Antioxidant
	High Molecular Weight
Uses	Piping
	Wire & Cable Applications
Forms	Pellets
Processing Method	Extrusion
	Pipe Extrusion

Physical	Nominal Value	Unit	Test Method
Density	0.950	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.10	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	63		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	130	°C	
CLTE - Flow	1.4E-4	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT