

Resblend PP/PA

Polyamide + PP

Polimarky Spolka Jawna

Message:

Resblend PP/PA is a Polyamide + PP (Nylon+PP) product. It is available in Europe.

General Information			
Physical	Nominal Value	Unit	Test Method
Density	0.960 to 1.05	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500 to 3300	MPa	ISO 527-2
Tensile Stress	39.0 to 42.0	MPa	ISO 527-2
Tensile Strain (Break)	40 to 55	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.5 to 5.5	kJ/m ²	ISO 179/1A
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	220 to 260	°C	
Mold Temperature	40.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

