

Kepital® ET-20A

Acetal (POM) Copolymer

KEP Americas

Message:

Carbon black filled conductive grade and surface resistivity is less than 10^4 ohm. It has good fuel and chemical resistance and it's suitable for fuel module parts.

General Information			
UL YellowCard	E120354-220439		
Additive	Carbon black		
Features	Good chemical resistance		
	Fuel resistance		
RoHS Compliance	RoHS compliance		
Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR)	1.0	g/10 min	ISO 1133
Molding Shrinkage - Flow (3.00 mm)	2.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	52.0	MPa	ISO 527-2
Nominal Tensile Strain at Break (23°C)	8.0	%	ISO 527-2
Flexural Modulus (23°C)	2450	MPa	ISO 178
Flexural Stress (23°C)	76.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.5	kJ/m²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	92.0	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+3	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

