# Starflex GM1810BB

### Metallocene Linear Low Density Polyethylene

#### LyondellBasell Industries

#### Message:

Starflex GM1810BB is a pelletized mLLDPE resin for use in applications that require maximum strength and toughness. GM1210BA contains a processing aid and antiblock, but does not contain slip.

General Information				
Additive	Processing aid			
	Anti-caking agent (4500 ppm)			
Features	High strength			
	Anti-caking property			
	Good toughness			
	Compliance of Food Exposure			
Uses	Films			
Agency Ratings	FDA 21 CFR 177.1520			
Forms	Particle			
Processing Method	Film extrusion			
Physical	Nominal Value	Unit	Test Method	
Density	0.921	g/cm <sup>3</sup>	ASTM D1505	
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238	
Films	Nominal Value	Unit	Test Method	
Film Thickness - Tested	19	μm		
secant modulus			ASTM D882	
1% secant, MD: 19 µm	186	MPa	ASTM D882	
1% secant, TD: 19 µm	193	MPa	ASTM D882	
Tensile Strength			ASTM D882	
MD: Break, 19 µm	67.6	MPa	ASTM D882	
TD: Break, 19 µm	59.3	MPa	ASTM D882	
Tensile Elongation			ASTM D882	
MD: Break, 19 µm	470	%	ASTM D882	
TD: Break, 19 µm	570	%	ASTM D882	
Dart Drop Impact <sup>1</sup> (19 µm)	600	g	ASTM D1709A	
Elmendorf Tear Strength			ASTM D1922	
MD : 19 µm	150	g	ASTM D1922	
TD : 19 μm	260	g	ASTM D1922	
Optical	Nominal Value	Unit	Test Method	
Gloss (45°, 19.1 µm)	45		ASTM D2457	

Haze (19.1 µm)	16	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	204 - 232	°C	
Extrusion instructions			
Blow-up ratio: 1.5 to 3			
NOTE			
1.	F50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

