

Sanren M800U (1st-grade)

Polypropylene Copolymer
SINOPEC Shanghai Petrochemical Co. Ltd.

Message:

The pellet product is ivory white and in the shape of a cylinder with satisfied strength, high abrasion resistance and low temperature resistance, high low-temperature impact strength and stress-fracture resistance, excellent chemical stability and insulating characteristics and fairly good heat resistance. Scope of Application: The basic material for household electric appliance parts and automobil parts.

General Information			
Features	Block Copolymer		
	High ESCR (Stress Cracking Resistance)		
	Good strength		
	Good wear resistance		
	Low temperature resistance		
	Low temperature impact resistance		
	Heat resistance, medium		
Uses	Home appliance components		
	Application in Automobile Field		
Appearance	White		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.3 - 11	g/10 min	Internal method
Ash Content		%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	> 18.6	MPa	ASTM D638
Flexural Modulus	> 800	MPa	Internal method
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	> 26	J/m	Internal method
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -45.0	°C	Internal method
Optical	Nominal Value	Unit	Test Method
Yellowness Index	< 4.0	YI	Internal method
Additional Information			
Cleanliness: 6-10 pieces/kg			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT