

Diamond ABS TM-40

Acrylonitrile Butadiene Styrene
Network Polymers, Inc.

Message:

Diamond ABS TM-40 is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in North America. Characteristics include:
Flame Rated
REACH Compliant
RoHS Compliant
WEEE Compliant
Heat Resistant

General Information			
Features	High Heat Resistance		
Agency Ratings	EC 1907/2006 (REACH)		
	EU 2002/96/EC (WEEE)		
RoHS Compliance	RoHS Compliant		
UL File Number	E150937		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	0.40	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	49.0	MPa	ASTM D638
Flexural Modulus - Tangent ²	2340	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 3.18 mm	114	°C	
1.8 MPa, Annealed, 3.18 mm	116	°C	
Vicat Softening Temperature	132	°C	ASTM D1525
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	2.0 to 4.0	hr	

Suggested Max Moisture	0.10	%
Rear Temperature	200 to 250	°C
Middle Temperature	200 to 250	°C
Front Temperature	200 to 250	°C
Mold Temperature	40.0 to 80.0	°C
Injection Pressure	48.3 to 75.8	MPa

NOTE

1. 51 mm/min
2. 1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

