

# RTP 799 X 112538

High Density Polyethylene

RTP Company

Message:

Permanently Anti-static - Masterbatch

General Information			
Features	Antistatic property		
Uses	Masterbatch		
RoHS Compliance	Contact manufacturer		
Processing Method	Blow molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0 - 20	g/10 min	ASTM D1238
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	193 - 232	°C	
Mold Temperature	21.1 - 65.6	°C	
Injection instructions			

Do not exceed 520 °F (270 °C) melt temperature.Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT