

SOLPLAST TH 7000C

Styrene Butadiene Styrene Block Copolymer

UTEKSOL d.o.o.

Message:

Is a commercial name for thermoplastic elastomers (TPE - S) based on SBS, SEBS (styrene - butadiene - styrene; styrene - ethylene butadiene - styrene) block copolymers, gathered with mixing SBS, SEBS, ... elastomers with polyolefines such as PP, PE, EVA, ...

Resistance to acid, bases and all aqueous solutions is excellent.

Resistance to alcohol and glycols is medium good.

Resistance to aromatic hydrocarbons, fat and of oil is bad.

Resistance round series upwards loosely increases.

All "SOLPLASTS" have a good electric-volume resistance: that's more than 1012 ohm-cm.

For coloring masters are used on a polyolefine base (PE, PP, EVA).

SERIES 7000

Technical compound on SBS block copolymers base;

Different physical characteristics and optics considering purpose of use.

Work temperature between - 50 in + 60° C.

For applications with no explicit exposure to the light (UV) and higher temperatures.

7000C

Replace for TPU

General Information			
Features	Acid Resistant		
	Base Resistant		
	General Purpose		
Uses	General Purpose		
Physical	Nominal Value	Unit	Test Method
Density	0.940 to 0.980	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR)	20 to 40	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A	75		
Shore D	40		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT