

UMG ALLOY® FA-820CA

Acrylonitrile Styrene Acrylate + PC

UMG ABS, Ltd.

Message:

UMG ALLOY® FA-820CA is an Acrylonitrile Styrene Acrylate + PC (ASA+PC) material. It is available in Asia Pacific or North America for injection molding.

Important attributes of UMG ALLOY® FA-820CA are:

Flame Rated

RoHS Compliant

General Information			
UL YellowCard	E47016-237302	E47016-237308	
RoHS Compliance	RoHS Compliant		
UL File Number	E47016		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.22	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	27.0	cm³/10min	ISO 1133
Molding Shrinkage - Flow (23°C)	0.10 to 0.30	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	122		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	8800	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	100	MPa	ISO 527-2
Flexural Modulus ¹ (23°C)	9000	MPa	ISO 178
Flexural Stress ² (23°C)	150	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	98.0	°C	ISO 75-2/Af
CLTE - Flow	1.5E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.800 mm	V-0		
1.70 mm	5VB		
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 105	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	220 to 240	°C	
Middle Temperature	240 to 260	°C	

Front Temperature	250 to 270	°C
Nozzle Temperature	240 to 260	°C
Processing (Melt) Temp	250 to 270	°C
Mold Temperature	60.0 to 80.0	°C
Injection Pressure	70.0 to 140	MPa
Injection Rate	Fast	
Back Pressure	5.00 to 15.0	MPa
Screw Speed	40 to 60	rpm

NOTE

1. 2.0 mm/min
2. 2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

