

Bayfit® 49BM02(80 Index, 79 kg/m³)

Polyurethane

Covestro - PUR

Message:

Polyol formulation intended for processing with isocyanates to produce visco-elastic moulded polyurethane foam with slow recovery after compression. Potential fields of application are mattresses and cushioning for the furniture industry.

General Information		
Uses	Furniture	
	Foam	
Forms	Liquid	
Physical	Nominal Value	Unit
Core Density	79.0	kg/m ³
Compression Hardness - cv40	2.20	
Hysteresis - h70	46	%
Elastomers	Nominal Value	Unit
Tensile Strength	0.118	MPa
Tensile Elongation (Break)	180	%
Tear Strength	0.245	kN/m
Compression Set ¹	3.3	%
Additional Information	Nominal Value	Unit
Hydroxyl Number, PET-11-01: 137 to 151 mg KOH/gWater Content, PET-19-01: 1.70 to 2.00%Density, PET-07-01: approx. 1.05 g/cm ³ Color: colorless, slightly yellowish, clearOdor: slightly like amineProcessing data (lab foaming): Temperature of raw materials: 25°C Cream Time: 11 sec Gel Time: 85 sec Rise Time: approx. 150 sec Mould Temperature: approx. 55°C Processing conditions for high pressure equipment: Mold Temperature: 50 to 60°C Molded Density: 70 to 95 kg/m ³ Mixing Ratios: 100:52 to 100:59 Demold Time: 6 to 7 min Temperature of raw materials: 20 to 30°C		
NOTE		
1.	at 75%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

