Interpol 47-5117/47-5205

Polyurethane (Polyester based)

Cook Composites and Polymers

Message:

Interpol 47-5117/47-5205 is a Polyurethane (Polyester based) (PUR-Ester) product. It can be processed by casting or injection molding and is available in North America.

Characteristics include:

Good Flexibility

Good Toughness

| General Information | | | |
|--|--------------------------|------|-------------|
| Features | Good Flexibility | | |
| | Good Toughness | | |
| | | | |
| Forms | Pellets | | |
| Processing Method | Casting | | |
| | Injection Molding | | |
| | | | |
| Hardness | Nominal Value | | Test Method |
| Durometer Hardness (Shore D) | 84 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 2450 | МРа | ASTM D638 |
| Tensile Strength (Yield) | 77.2 | МРа | ASTM D638 |
| Tensile Elongation (Yield) | 8.4 | % | ASTM D638 |
| Flexural Modulus | 3050 | MPa | ASTM D790 |
| Flexural Strength (Yield) | 131 | МРа | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 45 | J/m | ASTM D256 |
| Unnotched Izod Impact | 730 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 | | | |
| MPa, Unannealed) | 87.8 | °C | ASTM D648 |
| Thermoset | Nominal Value | Unit | |
| Thermoset Components | | | |
| Hardener | Mix Ratio by Weight: 27 | | |
| Resin | Mix Ratio by Weight: 100 | | |
| Demold Time (100°C) | 960 | min | |
| Injection | Nominal Value | Unit | |
| Mold Temperature | 54.4 to 65.6 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

