

4PROP® 25C10400

Polypropylene Copolymer

4Plas

Message:

4PROP 25C10400 is a MFI 10 to 14 UV Stabilised Copolymer Polypropylene

General Information			
Additive	UV stabilizer		
Features	Copolymer		
	Good UV resistance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
Molding Shrinkage			
Vertical flow direction	1.3	%	
Flow direction	1.3	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1300	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	28.0	MPa	ISO 527-2/5
Tensile Strain			ISO 527-2/5
Yield, 23°C	6.5	%	ISO 527-2/5
Fracture, 23°C	50	%	ISO 527-2/5
Flexural Modulus	1250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	2.5	kJ/m ²	ISO 179/1eA
0°C	3.0	kJ/m ²	ISO 179/1eA
23°C	5.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			ISO 180/1A
-30°C	2.0	kJ/m ²	ISO 180/1A
23°C	6.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	88.0	°C	ISO 75-2/B
1.8 MPa, not annealed	51.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	151	°C	ISO 306/A

--	67.0	°C	ISO 306/B
Melting Temperature ¹	165	°C	ISO 11357
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Ignition Temperature (2.00 mm)	650	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 - 240	°C	
Mold Temperature	20.0 - 50.0	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	40.0 - 80.0	MPa	
Screw Speed	400	rpm	
Injection instructions			
Feed Throat Temperature: 20 - 60 °C Back Pressure: Low			
NOTE			
1.	10 K/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

