

LNP™ THERMOCOMP™ KX97390 compound

Acetal (POM) Copolymer

SABIC Innovative Plastics

Message:

LNP THERMOCOMP* KX97390 is a compound based on Acetal Copolymer resin containing Glass Fiber. Added features of this material include:
Chemically Coupled.

Also known as: LNP* THERMOCOMP* Compound PDX-K-97390

Product reorder name: KX97390

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Chemically Coupled		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	1.2	%	ASTM D955, ISO 294-4
Across Flow : 24 hr	1.3	%	ASTM D955
Across Flow : 24 hr	1.2	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.10	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.35	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	4760	MPa	ASTM D638
--	5400	MPa	ISO 527-2/1
Tensile Strength			
Break	84.1	MPa	ASTM D638
Break	86.4	MPa	ISO 527-2
Tensile Elongation			
Break	3.2	%	ASTM D638
Break	3.4	%	ISO 527-2
Flexural Modulus			
--	4620	MPa	ASTM D790
--	5400	MPa	ISO 178
Flexural Strength			
--	124	MPa	ASTM D790
--	137	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	48	J/m	ASTM D256

23°C ²	5.3	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	430	J/m	ASTM D4812
23°C ³	33	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy	1.00	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	164	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	162	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	161	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Rear Temperature	177 to 188	°C	
Middle Temperature	193 to 204	°C	
Front Temperature	210 to 221	°C	
Processing (Melt) Temp	199 to 216	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT