

# Pro-fax PH350

Polypropylene Homopolymer

LyondellBasell Industries

## Message:

Pro-fax PH350 general-purpose polypropylene homopolymer is available in spherical particle form. This resin has very minimal stabilization, which allows wide design latitude in compounding applications. Additional stabilization is required to protect the resin during melt processing and throughout its useful life.

For regulatory compliance information see Pro-fax PH350 Product Stewardship Bulletin (PSB).

Please note that any additives compounded into this resin will require a re-assessment of its FDA status.

General Information			
Features	General Purpose		
	Good Stiffness		
	Homopolymer		
Uses	Compounding		
Forms	Spheres		
Processing Method	Compounding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm <sup>3</sup>	ASTM D792B
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	33.0	MPa	ASTM D638
Tensile Elongation (Yield)	12	%	ASTM D638
Flexural Modulus - 1% Secant <sup>2</sup>	1380	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	88.0	°C	ASTM D648
NOTE			
1.	50 mm/min		
2.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

