NaturePlast PBE 001

Thermoplastic Polyester

NaturePlast

Message:

Biopolyesters commercialized by Natureplast are thermoplastic resins 100% biodegradable and compostable in agreement with standards in use. Biopolyesters can also be partially biobased.

These biopolyesters can be processed on standard equipments.

Markets: bagging, film, food processing industry packaging, cosmetics, horticulture, medical, technical parts...

Properties

Translucency, processing easiness.

Performances close to polyolefins (PE and PP) in terms of thermal and mechanical properties.

Standard

| General Information | |
|---------------------|---------------------------------|
| Features | Biodegradable |
| | Compostable |
| | |
| Uses | Bags |
| | Cosmetics |
| | Engineering Parts |
| | Film |
| | Food Packaging |
| | Lawn and Garden Equipment |
| | Medical/Healthcare Applications |
| | |
| Appearance | Translucent |
| Forms | Pellets |
| Processing Method | Extrusion Blow Molding |
| | Film Extrusion |
| | Sheet Extrusion |
| | Thermoforming |
| | |

| Physical | Nominal Value | Unit | Test Method |
|----------------------------------|---------------|----------|-------------|
| Density | 1.24 | g/cm³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) | 4.5 | g/10 min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 290 | MPa | ISO 527-2 |
| Tensile Strain (Break) | > 590 | % | ISO 527-2 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Unnotched Impact Strength | No Break | | ISO 179 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

