Moplen H30S

Polypropylene Homopolymer

Shazand (Arak) Petrochemical Corporation

Message:

Aging

Oven Aging (150°C)

Moplen H30S is a very high flow polypropylene homopolymer with very narrow molecular weight distribution suitable for injection moulding and extrusion coating applications. Moplen H30S combines high stiffness with glossy coatings and good adhesion. Typical applications are high speed coating of woven polypropylene film yarn fabrics and paper coating. It is also well suited for injection moulding applications such as household articles, toys and packaging.

* Moplen H30S is suitable for food contact.

General Information					
Features	Food Contact Acceptable				
	Good Adhesion				
	High Flow				
	High Gloss				
	High Stiffness				
	Homopolymer				
	Narrow Molecular Weight Distribution				
Uses	Coating Applications				
	Fabric Coatings				
	Household Goods				
	Packaging				
	Paper Coatings				
	Toys				
Processing Method	Coating				
	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238		
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness (R-Scale)	93		ASTM D785		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	36.0	МРа	ASTM D638		
Tensile Elongation (Yield)	10	%	ASTM D638		
Flexural Modulus	1600	МРа	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact (23°C)	30	J/m	ASTM D256		

Unit

day

Test Method

ASTM D3012

Nominal Value

15.0

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ((0.45		
MPa, Unannealed)	96.0	°C	ASTM D648
Vicat Softening Temperature	154	°C	ASTM D1525 ¹
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

