

Double Elephant SX-302

Polymethyl Methacrylate Acrylic
Suzhou Double Elephant Optical Material Co., LTD.

Message:

Molding compound with normal flow property, good heat resistance and mechanical strength.
Application: the products with simple shape and requiring good heat resistance, such as magnifying glass, nameplate, indicator and container.

General Information			
Features	Good Flow		
Uses	Containers		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	6.0	g/10 min	ISO 1133
Water Absorption (Saturation, 23°C)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	71.0	MPa	ISO 527-2
Tensile Strain (Break)	4.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.5	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	95.0	°C	ISO 75-2/A
Vicat Softening Temperature	103	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+16	ohms	
Volume Resistivity	> 1.0E+14	ohms·cm	GB/T 1410
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ISO 489
Transmittance	92.0 to 93.0	%	ISO 13468

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

