# Generic Rubber

### Rubber

Generic

#### Message:

This data represents typical values that have been calculated from all products classified as: Generic Rubber This information is provided for comparative purposes only.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.888 to 1.94	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	0.621 to 4.14	MPa	ASTM D638
Thermoset	Nominal Value	Unit	
Post Cure Time	2.0 to 2.1	hr	
Uncured Properties	Nominal Value	Unit	
Density (23°C)	1.10 to 1.21	g/cm³	
Cured Properties	Nominal Value	Unit	
Shore Hardness (23°C)	25 to 70		
Tensile Strength (23°C)	8.26 to 10.0	MPa	
Tensile Elongation at Break (23°C)	440 to 810	%	
Tear Strength (23°C)	12.3 to 39.4	kN/m	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

