

Lupolen 1800 P

Low Density Polyethylene

LyondellBasell Industries

Message:

Lupolen 1800 P is a low density polyethylene (LDPE) resin used in injection molding and other processing methods. It exhibits high flowability, and good softness, toughness and dimensional stability. Lupolen 1800 P is delivered in pellet form and is not additivated. Lupolen 1800 P is used in applications such as compounding, toys, caps & closures, engineering parts, and sports and leisure equipment. Lupolen 1800 P is not intended for use in medical and pharmaceutical applications.

General Information			
Features	Fast Molding Cycle		
	Good Dimensional Stability		
	Good Flexibility		
	Good Processability		
	Good Toughness		
	High Flow		
	Low Temperature Impact Resistance		
Uses	Caps		
	Closures		
	Compounding		
	Engineering Parts		
	Sporting Goods		
Forms	Pellets		
Processing Method	Compounding		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.918	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance ¹	2.00	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	45		ISO 868
Ball Indentation Hardness	12.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	200	MPa	ISO 527-2
Tensile Stress (Yield)	9.00	MPa	ISO 527-2
Thermal	Nominal Value	Unit	Test Method

Vicat Softening Temperature	80.0	°C	ISO 306/A50
Melting Temperature (DSC)	105	°C	ISO 3146
Extrusion	Nominal Value	Unit	
Melt Temperature	180 to 230	°C	
NOTE			
1.	Tested in 10% nonionic surfactants		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

