

Monprene® RG-20160 X (PRELIMINARY DATA)

Thermoplastic Elastomer

Teknor Apex Company

Message:

Monprene RG-20160 is specifically designed for regulated applications including food contact, toys, and children's products. This grade is suitable for extrusion. Monprene RG-20160 complies with various US FDA and European regulations and directives for food contact and toy safety. Please contact Teknor Apex for a regulatory compliance letter.

General Information			
Features	Low Specific Gravity		
	Without Fillers		
	Low density		
	smoothness		
	Low liquidity		
	Lubrication		
	Compliance of Food Exposure		
	BPA-free		
	No kinetic components		
Uses	Medium hardness		
	Cosmetic Packaging		
	Kitchen utensils		
	Non-specific food applications		
	Cover		
	Food packaging		
	Food service sector		
	Food container		
	Toys		
Agency Ratings	Consumer goods application field		
	FDA Food Exposure, Not Rated		
Appearance	European food contact, not rated		
	Translucent		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.886	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.5	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	60		ISO 868

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹			ISO 37
Transverse flow: 100% strain	1.80	MPa	ISO 37
Flow: 100% strain	4.00	MPa	ISO 37
Tensile Stress ²			ISO 37
Transverse flow: Fracture	9.00	MPa	ISO 37
Flow: Fracture	4.00	MPa	ISO 37
Tensile Elongation ³			ISO 37
Transverse flow: Fracture	800	%	ISO 37
Flow: Fracture	150	%	ISO 37
Compression Set ⁴			ISO 815
23°C, 22 hr	16	%	ISO 815
70°C, 22 hr	28	%	ISO 815
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 206 sec ⁻¹)	286	Pa · s	ASTM D3835
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	149 - 160	°C	
Cylinder Zone 2 Temp.	160 - 204	°C	
Cylinder Zone 3 Temp.	171 - 216	°C	
Cylinder Zone 4 Temp.	182 - 227	°C	
Die Temperature	182 - 227	°C	
Extrusion instructions			
Screw Speed: 30 to 100 rpmDrying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150F (65C).			
NOTE			
1.	Type 1, 510mm/min		
2.	Type 1, 510mm/min		
3.	Type 1, 510mm/min		
4.	Type a		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT