

# Maxxam™ PPH-40G Black

Polypropylene Homopolymer

PolyOne Corporation

## Message:

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

General Information			
UL YellowCard	E76261-101413513		
Filler / Reinforcement	Filler,40% Filler by Weight Glass Fiber		
Features	General Purpose Homopolymer		
Uses	Automotive Applications Construction Applications Consumer Applications General Purpose Industrial Applications		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm <sup>3</sup>	ASTM D792
Specific Volume	0.820	cm <sup>3</sup> /g	ASTM D792
Molding Shrinkage - Flow	0.10 to 0.40	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	99		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	70.3	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	5.0	%	ASTM D638
Flexural Modulus	6550	MPa	ASTM D790
Flexural Strength	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	53	J/m	ASTM D256A
Unnotched Izod Impact <sup>3</sup> (23°C, 3.18 mm)	150	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Annealed, 3.18 mm)	162	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, ALL)	HB		UL 94
NOTE			
1.	Type I, 51 mm/min		
2.	Type I, 51 mm/min		
3.	Injection Molded		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

