

Formolon® NVA

Polyvinyl Chloride

Formosa Plastics Corporation, U.S.A.

Message:

F-NVA is a high molecular weight PVC dispersion resin with low residual surfactant content.

Plastisols containing F-NVA exhibit low paste viscosities and good viscosity stability. This product is presently being utilized in a variety of applications where the resulting films or coating require high tensile strength and resistance to abrasion.

General Information			
Features	Dispersible		
	Good Abrasion Resistance		
	High Molecular Weight		
	High Strength		
	Homopolymer		
	Low Residuals		
	Low Viscosity		
Uses	Coating Applications		
	Film		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Pellets		
Processing Method	Coating		
Physical	Nominal Value		Test Method
K-Value	80.0		
Inherent Viscosity	1.3		ASTM D1243
Relative Viscosity ¹	2.90		
Brookfield Viscosity			
-- ²	4.50	Pa · s	
-- ³	5.50	Pa · s	
Sever Viscosity ⁴	8.00	Pa · s	
Gel Temperature ⁵	91	°C	
Methanol Extractables	1.5	%	ASTM D2222
Volatiles	0.30	%	ASTM D3030
NOTE			
1.	QC-10-104		
2.	SPI-VD-T1, 20 rpm, aged 2 hrs		
3.	SPI-VD-T1, 2 rpm, aged 2 hrs		
4.	SPI-VD-T2, 100 psig aged 2 hrs		
5.	SPI-VD-T18		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

