

# Viton® GF-200S

Fluoroelastomer

DuPont Performance Elastomers

## Message:

Peroxide Curable Gum Polymers - made with Advanced Polymer Architecture technology  
25 Mooney, low viscosity peroxide curable GF-type gum.

General Information	
Features	Low viscosity
	Solvent resistance
	Compliance of Food Exposure
Uses	Washer
	Pipe
	Pipe fittings
	Metal bonding
	Seals
	Coating application
Agency Ratings	FDA 21 CFR 177.2600 2
Forms	Particle
Processing Method	Extrusion
	Resin transfer molding
	Coating
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.90	g/cm <sup>3</sup>	ASTM D792
Mooney Viscosity	25	MU	ASTM D1646
Elastomers	Nominal Value	Unit	Test Method
Compression Set (200°C, 70 hr)	25	%	ASTM D395
Additional Information			

Nominal Viscosity, ML 1 + 10, 121°C: 25Polymer Fluorine Content: 70.2%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

