

LNP™ LUBRICOMP™ DX96651 compound

Polycarbonate

SABIC Innovative Plastics

Message:

LNP LUBRICOMP* DX96651 is a compound based on Polycarbonate resin containing Proprietary Filler(s). Added feature of this material is: Wear Resistant.

Also known as: LNP* LUBRICOMP* Compound PDX-D-96651 SF

Product reorder name: DX96651

General Information			
UL YellowCard	E121562-101343437		
Filler / Reinforcement	Proprietary		
Features	Good Wear Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.70	%	ASTM D955
Across Flow : 24 hr	0.70	%	ASTM D955
Across Flow : 24 hr	0.75	%	ISO 294-4
Flow : 24 hr	0.73	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.16	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2210	MPa	ASTM D638
--	2400	MPa	ISO 527-2/1
Tensile Strength			
Yield	48.5	MPa	ASTM D638
Yield	55.0	MPa	ISO 527-2
Break	58.6	MPa	ASTM D638
Break	46.8	MPa	ISO 527-2
Flexural Modulus			
--	2480	MPa	ASTM D790
--	2600	MPa	ISO 178
Flexural Strength			
--	93.5	MPa	ASTM D790
--	90.7	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	100	J/m	ASTM D256
23°C ²	9.2	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			

23°C	No Break		ASTM D4812
23°C ³	140	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	41.0	J	ASTM D3763
--	128	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.20 mm	140	°C	
1.8 MPa, Unannealed, 3.20 mm	128	°C	
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	6.6E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.6E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	V-2		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 to 304	°C	
Middle Temperature	304 to 316	°C	
Front Temperature	310 to 321	°C	
Processing (Melt) Temp	299 to 316	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT