

# Wah Hong UP WH-8100-BLK FDA

Polyester Alloy

Wah Hong Industrial Corp.

Message:

Dry BMC material is Wah Hong Thermoset Plastic, which separate to UP & DAP two types. UP & DAP molding compounds with the excellent properties of moldability, dimemsional stability, electric characteristics, mechanical strength, and heat resistance. Especially, the dry molding compounds pellet can be widely applied in the injection products such as electronics, automobile parts, and household electric appliances.

General Information			
Features	Flame Retardant		
	Food Contact Acceptable		
	Good Dimensional Stability		
	Good Electrical Properties		
	Good Moldability		
	Good Strength		
	Halogen Free		
	High Heat Resistance		
	Low Shrinkage		
Uses	Automotive Electronics		
	Electrical/Electronic Applications		
	Food Containers		
	Support Trays		
Agency Ratings	FDA Unspecified Rating		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.91	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.22 to 0.25	%	ASTM D955
Water Absorption (23°C, 24 hr)	< 0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	12700 to 13700	MPa	ASTM D790
Flexural Strength	113 to 123	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	265	°C	ASTM D648
CLTE - Flow	3.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ASTM D257
-- 1	1.0E+13 to 1.0E+14	ohms·cm	
-- 2	1.0E+14 to 1.0E+15	ohms·cm	
Dielectric Strength	30 to 33	kV/mm	ASTM D149
Arc Resistance	180	sec	ASTM D495
Comparative Tracking Index (CTI)	> 600	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
NOTE			
1.	Boiling		
2.	Normal		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

