

Alathon® L5840AS

High Density Polyethylene
LyondellBasell Industries

Message:

ALATHON L 5840AS is a lightweighting resin that exhibits excellent color, low odor and provides processing stability. Typical applications include household chemicals, industrial chemicals, detergent, and motor oil bottles. L 5840AS contains antistat.

General Information			
Additive	Antistatic property		
Features	Antistatic property		
	Good processing stability		
	The smell is low to none		
	Compliance of Food Exposure		
Uses	Bottle		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Particle		
Processing Method	Blow molding		
Physical	Nominal Value	Unit	Test Method
Density	0.958	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.35	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 10% Igepal CO-630, F50)	25.0	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	68		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.3	MPa	ASTM D638
Tensile Elongation (Break)	> 600	%	ASTM D638
Flexural Modulus	1450	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Tensile Impact Strength	294	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	81.0	°C	ASTM D648
Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	128	°C	ASTM D1525
Additional Information			

Elongation at Break, ASTM D638: >600%Tensile Impact, ASTM D1822: 140 ft-lb/in

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT