SILVER® ABS 313NL

Acrylonitrile Butadiene Styrene

Guangdong Silver Age Sci & Tech. Co., Ltd

Message:

SILVER® Modified ABS is applied to many fields, such as computer fittings, OA equipment and fittings, appliance crust and electronic fittings. In addition, the custom—made products should be developed by buyers 'requirements in order to meet special usage.

ARS

Characteristics:

easy molding, good heat resistance

Application:

soymilk case, heater case, auto parts

| General Information | | | |
|--|-------------------------|----------|-------------|
| Features | Good Moldability | | |
| | Medium Heat Resistance | | |
| Uses | Automotive Applications | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.05 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (220°C/10.0 kg) | 5.0 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ | 40.0 | MPa | ASTM D638 |
| Tensile Elongation ² (Break) | 15 | % | ASTM D638 |
| Flexural Modulus ³ | 2100 | MPa | ASTM D790 |
| Flexural Strength ⁴ | 65.0 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (Area) (23°C) | 20.0 | kJ/m² | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 98.0 | °C | ASTM D648 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating | НВ | | UL 94 |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 210 to 240 | °C | |
| NOTE | | | |
| 1. | 50 mm/min | | |
| 2. | 50 mm/min | | |
| 3. | 5.5 mm/min | | |
| 4. | 5.5 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2