

EL-Lene™ H6670B

High Density Polyethylene
SCG Chemicals Co., Ltd.

Message:

EL-Lene H6670B is a high density polyethylene resin suitable for producing milk bottles by using Extrusion blow molding machine.

General Information			
Features	Excellent Printability		
	Food Contact Acceptable		
	Good Flow		
	Good Processability		
	High Stiffness		
	Low to No Odor		
Uses	Bottles		
	Fruit Juice Bottles		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Extrusion Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.966	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.70	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 25% Igepal, Compression Molded, F50)	24.0	hr	ASTM D1693B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	68		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	31.4	MPa	
Break	32.4	MPa	
Tensile Elongation ² (Break)	1200	%	ASTM D638
Flexural Modulus	1470	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -60.0	°C	ASTM D746
Vicat Softening Temperature	128	°C	ASTM D1525
Melting Temperature	132	°C	ASTM D2117

Extrusion	Nominal Value	Unit
Melt Temperature	170 to 180	°C
NOTE		
1.	50 mm/min	
2.	50 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

