

# BESTNYL SI00VI01BW

Polyamide 6

Triesa Plastics

## Message:

Polyamide 6 natural lubrified with V-0 free halogen quality, normally used in electrical appliances, for its easy injection and mould release as well as its excellent flame resistance.

General Information			
Additive	Lubricant		
Features	Flame Retardant		
	Good Mold Release		
	Halogen Free		
	Lubricated		
Uses	Appliances		
	Electrical/Electronic Applications		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage	1.1 to 1.4	%	ISO 294-4
Water Absorption (23°C, 24 hr)	1.5	%	ISO 62
Humidity - Pellets	< 0.20	%	ISO 1110
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	78		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3000	MPa	ISO 527-2
Tensile Stress	70.0	MPa	ISO 527-2
Tensile Strain (Break)	5.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	200	°C	ISO 75-2/B
1.8 MPa, Unannealed	75.0	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Electric Strength	16	kV/mm	IEC 60243-1

Comparative Tracking Index	550	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating	V-0		UL 94
Glow Wire Ignition Temperature	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	225 to 240	°C	
Mold Temperature	60.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

