S-RIM™ 6260 Black

Thermoplastic

Hapco Inc.

Message:

S-RIM™ 6260 Black is a Thermoplastic product. It can be processed by structural react. inject. molding (srim) and is available in North America. Characteristics include:

Fast Molding Cycle

Heat Resistant

General Information				
Features	Fast Molding Cycle			
	High Heat Resistance			
Appearance	Black			
Forms	Liquid			
Processing Method	Structural React. Inject. Molding (SRIM)			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.12	g/cm³	ASTM D4669	
Molding Shrinkage - Flow	0.40 to 0.80	%	ASTM D2566	
Weight - per cubic inch	18	g		
Gel Time ¹ (25°C)	1.0	min	ASTM D2971	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D)	80		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Modulus	655	MPa	ASTM D638	
Tensile Strength	53.1	MPa	ASTM D638	
Tensile Elongation (Break)	15	%	ASTM D638	
Flexural Modulus	1820	MPa	ASTM D790	
Flexural Strength	73.1	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact	9.6	J/m	ASTM D256	
Unnotched Izod Impact	56	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
0.45 MPa, Unannealed ²	189	°C		
0.45 MPa, Unannealed ³	108	°C		
1.8 MPa, Unannealed ⁴	117	°C		
1.8 MPa, Unannealed ⁵	157	°C		
Thermoset	Nominal Value	Unit	Test Method	
Thermoset Components				
Part A	Mix Ratio by Weight: 100, Mix	Mix Ratio by Weight: 100, Mix Ratio by Volume: 100		

Part B	Mix Ratio by Weight: 86, Mix Ratio by Volume: 100		
Thermoset Mix Viscosity (25°C)	600	сР	ASTM D4878
Demold Time (21°C)	5.0 to 12	min	Internal Method
NOTE			
1.	100 g		
2.	post cured at 140°C		
3.	post cured at 80°C		
4.	post cured at 80°C		
5.	post cured at 140°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

