

# Petlon Prime A1-00-00-NT

Polyamide 6

Petlon Polymers Ltd

## Message:

Prime Nylon 6, Natural, Lubricated Compound.

General Information			
Additive	Lubricant		
Features	Lubricated		
Appearance	Natural Color		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm <sup>3</sup>	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	95.0	MPa	ISO 527-2
Tensile Strain (Break)	3.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	8.0	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Flammability	Nominal Value		Test Method
Flame Rating	V-2		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	240 to 270	°C	
Mold Temperature	50.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT