# **COPYLENE® CH120LN**

### Polypropylene Homopolymer

Phillips 66

#### Message:

COPYLENE® CH120LN is designed for general purpose injection molding applications with anit-static and nucleation.

Applications:

**Food Containers** 

Housewares

Closures

General Information			
UL YellowCard	E338982-101025806		
Additive	Antistatic		
	Nucleating Agent		
Features	Antistatic		
	Homopolymer		
	Nucleated		
Uses	Closures		
	Food Containers		
	Household Goods		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	37.6	MPa	ASTM D638
Tensile Elongation (Yield)	7.0	%	ASTM D638
Flexural Modulus - 1% Secant <sup>2</sup>	1760	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	43	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	119	°C	ASTM D648
NOTE			
1.	51 mm/min		
2.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

