

RTP 287 TFE 10

Polyamide 66

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
RTP 280 TFE Series are carbon fiber reinforced nylon 6/6 lubricated with PTFE. They are characterized by excellent physical properties, wear resistance and static dissipation capacity.
-Preliminary Product Data per RTP Co.-
The value listed as Flammability, UL 94, was tested in accordance with RTP test standards.

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 40% filler by weight		
Additive	PTFE lubricant (10%)		
Features	Conductivity		
	High strength		
	Good chemical resistance		
	Good wear resistance		
	Lubrication		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.40	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	29000	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	241	MPa	ASTM D638
--	228	MPa	ASTM D638
Tensile Elongation (Break)	1.5	%	ASTM D638
Flexural Modulus	23400	MPa	ASTM D790
Flexural Strength			ASTM D790

--	348	MPa	ASTM D790
Yield	365	MPa	ASTM D790
Compressive Strength	165	MPa	ASTM D695
Coefficient of Friction (With Metal-Dynamic)	0.16		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	110	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	750	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	260	°C	ASTM D648
1.8 MPa, not annealed	260	°C	ASTM D648
CLTE - Flow	1.4E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	1.2	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+5	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Additional Information			
Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 2mil/in.The coefficient of friction was tested on a Falex Model No.6 Wear Testing Machine at 50 FPM, 2000 PV, against C1018 steel of hardness 15-25 Rockwell C, 14-17 micro smoothness.			
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Suggested Max Regrind	20	%	
Rear Temperature	274 - 288	°C	
Middle Temperature	274 - 288	°C	
Front Temperature	274 - 288	°C	
Mold Temperature	65.6 - 107	°C	
Injection Pressure	82.7 - 124	MPa	
Back Pressure	0.172 - 0.345	MPa	
Screw Speed	50 - 90	rpm	
Clamp Tonnage	6.2 - 9.7	kN/cm ²	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

