

Latamid 66 H2 G/25-V0CT4

Polyamide 66

LATI S.p.A.

Message:

Polyamide 66 (PA66) based compound.

Heat stabilised. Glass fibres. UL94 V-0 classified, with brominated flame retardants, PBB/PBDE free.

General Information	
UL YellowCard	E54080-100987625
Filler / Reinforcement	Glass Fiber,25% Filler by Weight
Additive	Flame Retardant
	Heat Stabilizer
Features	Brominated
	Flame Retardant
	Heat Stabilized
Agency Ratings	NF F 16-101
	NF F 16-102

Physical	Nominal Value	Unit	Test Method
Density	1.82	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.80 to 1.1	%	
Flow : 2.00 mm	0.40 to 0.70	%	
Water Absorption (23°C, 24 hr)	0.26	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9200	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	75.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.4	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	50	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	240	°C	ISO 75-2/B
1.8 MPa, Unannealed	185	°C	ISO 75-2/A
Continuous Use Temperature ²	115	°C	
Vicat Softening Temperature	220	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	7.0E-6	cm/cm/°C	ISO 11359-2

Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-0		
1.50 mm	V-0		
3.00 mm	V-0		
Glow Wire Flammability Index			IEC 60695-2-12
1.00 mm	960	°C	
2.00 mm	960	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
1.00 mm	825	°C	
2.00 mm	875	°C	
Oxygen Index	34	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0	hr	
Suggested Max Regrind	15	%	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	70.0 to 100	°C	
Injection Rate	Moderate		
NOTE			
1.	60 MPa		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT